



PAPER FOR POS AND CASH REGISTER

Technical data sheet

Physical properties	Value	Unit	Test Method
Baseweight	55 ± 4	g/m ²	ISO 536
Caliper	60 ± 5	µm	ISO 534
Smoothness (Bekk)	> 260	sec	ISO 5627
Brightness (R457)	> 87	%	DIN53145-2
Opacity	> 85	%	ISO 2471
Stiffness md	> 47	mNm	ISO 1924/2
Stiffness cd	> 85	mNm	ISO 1924/2

Grade Characteristics	Value
Sensitivity	Standard
Printing speed	200 mm/sec
Protection coating	Without topcoating
Image durability	7 years

Climatic stability	Value
Heat resistance	60°C / 24
Humidity Resistance	40° C / 90% r.h./ 24h